

Table 2

## Characteristics of major non-exploited brown coal deposits

	Name of deposit	Thickness of coal seams (in m)	Depth to the base	Overburden-to deposit thickness ratio	Calorific value (kcal/kg)	Ash content (%)	Mean. content of sulfur (%)
1	Babina - Żarki	10.7	140.0	-	2,229	18.28	1.10
2	Cybinka	8.8	78.0	7.9	2,251	17.16	1.32
3	Gubin	7.6	99.7	28.9	2,240	12.86	1.42
4	Głowaczów	4.8	37.1	6.5	1,820	28.56	0.42
5	Legnica-pole Północ	22.0	207.2	8.7	2,194	18.72	1.42
6	Legnica-pole Wschód	18.1	155.4	7.6	2,090	21.80	0.42
7	Legnica-pole Zachód	21.0	158.8	6.6	2,254	18.14	0.74
8	Mosty	9.1	82.7	8.0	2,219	17.19	1.63
9	Piaski	6.1	48.5	7.3	2,072	24.90	1.44
10	Rogóżno	18,7	104,5	4,9	2,241	24,54	3,79
11	Rzepin	12.2	97.3	7.9	2,164	15.14	1.20
12	Sądów	12.2	127.5	10.2	2,196	19.16	1.39
13	Ścinawa	20.2	207.1	8.9	2,275	12.88	0.64
14	Torzym	21.4	180.8	7.9	2,270	16.80	1.81
15	Trzcianka	4.2	45.9	11.9	2,004	23.07	1.84
16	Złoczew	51.4	266.6	5.0	1,968	21.29	2.14